



1001 Trout Brook Crossing
 Rocky Hill, CT 06067-3910
 Telephone: (860) 571-5100
 FAX: (860) 571-5465

Technical Data Sheet

Product 5145

Worldwide Version, October 1995

PRODUCT DESCRIPTION

LOCTITE® Product 5145 is a non-corrosive, paste consistency, high strength, RTV silicone. When cured the elastomer resists weathering, moisture and ozone, and retains its flexibility up to 200°C. Meets requirements of MIL-A-46146B Group II Type I.

TYPICAL APPLICATIONS

Specifically formulated for bonding, sealing and coating of electronic devices, especially for military, automotive and industrial electronics. The non-slumping nature of this product makes it ideal for reinforcing and strain relieving delicate components.

PROPERTIES OF UNCURED MATERIAL

	Typical Value
Chemical Type	Alkoxy Silicone Rubber
Appearance	Translucent paste
Specific Gravity @ 25°C	1.14
(@ 25°C, 0.6 Mpa, 3.2mm orifice)	200

TYPICAL PROPERTIES OF CURED MATERIAL

Physical Properties

(cured 7 days @ 50% RH & 23°C)	
Coefficient of thermal expansion, ASTM E831, /°C ⁻¹	2.8 x 10 ⁻⁴
Thermal Conductivity, W/m °C, ASTM E1225	0.20
Tensile Strength, ASTM D412, N/mm ²	7
(psi)	(1000)
Elongation, ASTM D412, %	750
Hardness, ASTM D2240, Shore A	33
Water absorption, 24hrs. @ RT., ASTM D570, %	0.01
Tear (die B), ASTM D624, KN/m	40
(pli)	(230)
Non-volatile content, MIL-46106 A, %	96
Water vapor transmission, ASTM E96, gram/hr./M ²	0.48

Electrical Properties

	Constant	Loss
Dielectric constant & loss, ASTM D150, 25°C		
@ 100 Hz	3.0	0.006
@ 1 MHz	3.1	0.010
Volume Resistivity, ASTM D257, Ω.cm		4 x 10 ¹⁵
Dielectric Strength, ASTM D149, kV/mm, 4mm film		18

PERFORMANCE OF CURED MATERIAL

(cured 7 days @ 50% RH & 23°C)

Peel Adhesion, pli Method, ASTM D903	
Primed Aluminum	75
Primed Steel	50

TYPICAL ENVIRONMENTAL RESISTANCE

The following tests refer to the effect of environment on strength. This is not a measure of sealing performance.

Heat Resistance

(7 days @ 200°C)

Tensile strength, ASTM D412, N/mm ² (psi)	3 (500)
Elongation, ASTM D412, %	330
Hardness, Shore A, ASTM D2240	45

Hydrolytic Stability

(After 28 days @ 95°C & 98% RH)

Tensile strength, ASTM D412, N/mm ² (psi)	5 (700)
Elongation, ASTM D412, %	500
Hardness, Shore A, ASTM D2240	29

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Where aqueous washing systems are used to clean the surfaces before bonding, it is important to check for compatibility of the washing solution with the adhesive. In some cases these aqueous washes can affect the cure and performance of the adhesive.

Directions for use

For best performance surfaces should be clean and free of grease or other contaminants. Full performance properties will develop over 72 hours. Moisture curing begins immediately after the product is exposed to the atmosphere, therefore parts to be assembled should be mated within a few minutes after the product is dispensed. Excess material can be easily wiped away with non-polar solvents.

In case of eye contact flush at least 15 minutes with water and seek medical attention. To avoid contact use the applicator nozzle provided.

Storage

Product shall be ideally stored in a cool, dry location in unopened containers at a temperature between 8°C to 28°C (46°F to 82°F) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused product, do not return any material to its original container. For further specific shelf life information, contact your local Technical Service Center.

Data Ranges

The data contained herein may be reported as a typical value and/or range. Values are based on actual test data and are verified on a periodic basis.

Note

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Loctite Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Loctite Corporation's products. Loctite Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Loctite Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

NOT FOR PRODUCT SPECIFICATIONS
 THE TECHNICAL DATA CONTAINED HEREIN ARE INTENDED AS REFERENCE ONLY.
 PLEASE CONTACT LOCTITE CORPORATION QUALITY DEPARTMENT FOR ASSISTANCE AND RECOMMENDATIONS ON SPECIFICATIONS FOR THIS PRODUCT.
 ROCKY HILL, CT FAX: +1 (860)-571-5473 DUBLIN, IRELAND FAX: +353-(1)-451-9959